



## BY-LUX VISIBLE PENETRANT

### Technical Data Sheet

**Description:** **BY-LUX** is water washable visible penetrant used to locate cracks, laps, pores, lack of bonding, and similar surface flaws. **BY-LUX** can be used on insoluble nonporous parts including both ferrous and nonferrous metals, ceramics, and glass and some plastics. Referred to as the “visible dye penetrant” method or “color contrast” method of inspection and can be used for weld inspection.

### Chemical Properties

Color: Red  
Viscosity: 5.20 cSt @ 100°F  
Flash Point: 210°F (98°C)  
Fluorescence: Yellow/Green  
Water Tolerance: 14%

### Companion Products

D-100 Non-Aqueous Developer                      DR-62 Solvent Remover  
DR-60 Solvent Remover

### Packaging

One Gallon Cans                      55 Gallon Drums  
Five Gallon Cans                      16oz. Aerosol Cans (9 cans per case)

### Storage /Shelf Life

Keep away from moisture and sunlight.  
Temperature limit: 40°F to 125°F (0-50°C)  
Keep the container closed when not in use.  
Shelf life from invoice date: Bulk Container – 36 months

### Specifications

MIL-I-25135 Revisions C      ASME Code NDT, Sec V

### Special Features

1. Brings flaws into sharper, clearer focus with more intense red color.
2. Performs more reliably over a greater range of temperatures.
3. **BY-LUX** meets stringent low sulfur and chloride requirements.
4. Long lasting flaw mark indications; less fading.
5. Water washable; easy to remove.
6. **BY-LUX** indications fluoresce orange under black light.
7. **BY-LUX** is compatible with fluorescent penetrants.



## Instructions

**Note:** These instructions describe the basic process, but they may need to be amended by the user to comply with applicable specification and/or inspection criteria provided by the contracting agency.

1. **Application:** Apply **BY-LUX** only to clean, dry surfaces by spraying, flowing, brushing or dipping.

2. **Dwell Time:** A 10 minute dwell time is suggested, although in many cases five minutes will suffice. When particularly tight cracks are suspected, or the part is especially critical, the dwell time may be extended to 30 minutes, or longer. Allow the penetrant to drain from the part surface back into the penetrant tank to conserve material.

3. **Removal:**

**A) Water Wash Method** - Use ambient temperature water to rinse **BY-LUX** from the part surface. To avoid washing entrapped penetrant from surface flaws, do not use high water pressure temperatures and avoid prolonged washing times.

**B) Solvent Wipe Method** - Remove as much excess penetrant as possible using a clean, dry rag or toweling. Remove remaining penetrant film by wiping with a rag or toweling that has been slightly moistened with solvent. Use a minimum of solvent; avoid flushing penetrant from flaws. Do not spray solvent directly on the part surface when removing excess penetrant. Rough surfaces require more generous application of solvent.

4. **Drying:**

**A)** A re-circulating oven set no higher than 160<sup>0</sup>F (71<sup>0</sup>C) is suggested. Leave the part in the oven just long enough to evaporate surface moisture. Drying is improved by using pressurized air to disperse and remove as much excess water as possible before placing the part in to the oven.

**B)** When solvent remover is used, allow the surface to dry completely before applying developer.

5. **Developing:** Apply the developer by spray using the appropriate developer. Flaw marks are visible under black light almost immediately, but allow sufficient developing time to enhance the flaw visibility.

6. **Inspection:** Inspect parts under appropriate light.

## Health & Safety

**BY-LUX** is a combustible liquid. Use with adequate ventilation and away from sparks, fire or open flames. Avoid prolonged or repeated contact with skin. Do not take internally. Consult the MSDS for more safety and health information.